

1. Test method

• The University of Pittsburgh Test Protocol (Upitt)

For Measurement of Acute Lethality of Thermal Decomposition Products of Specimens

The major function of the UPitt laboratory test method is to provide a means of evaluating the lethal toxic potency of thermal decomposition products of test materials.

• Test procedure:

The test protocol call for samples to be subjected to continuously changing temperature conditions starting at 30°C and increasing at a rate of 20°C/min.

The test system generates decomposition products that continuously change in chemical composition as the temperature increases.

Animals are exposed to the decomposition products starting when the test sample loses one percent of its initial weight and continues for 30 min.

The UPitt protocol utilizes rodent (mouse) lethality as the primary source in evaluating the toxicity of combustion atmosphere produced by a material.

Groups of four animals at a time are exposed to the combustion gases generated from different initial quantities of the test material.

This establishes a concentration-response relationship. From this relationship, the concentration estimated to produce lethality in 50 percent of the animals within the specified time is obtained by interpolation.

This concentration, commonly termed the LC50, is a measure of the toxic potency of combustion atmosphere.

• Evaluation:

The Building Code of the City of New York requires the materials to be “not more toxic than wood,” which requires a passing LC50 value of greater than or equal to 19.7g

2. Test result

TEST SAMPLE	LC ₅₀ value
Solid Color	84.4g
Patterned Color	81.8g

Thermal decomposition of Staron® Solid Surfaces was measured at a temperature greater than 300°C (572°F), which is most likely in case of fire. Staron® Solid Surfaces meet the requirements for interior finish material as defined by Title 27, Chapter 1, Subchapter 5, Article 5, of the Building Code of the City of New York.

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of Lotte Chemical Corp. products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, Lotte Chemical Corp. assumes no responsibility for its suitability or accuracy or the use of such information for products other than Lotte Chemical Corp. Staron® solid surfaces & Radianz® quartz surfaces.